## **TECHNICAL DATA SHEET**

# CHRYSO<sup>®</sup> SCREEDFINISH EBA 20

**Evaporation Reducing Agent** 

## DESCRIPTION

CHRYSO® ScreedFinish EBA 20 is a water based evaporation barrier agent, ready to use & specifically designed to enhance CHRYSO® Cemfloor & Mobicem screeds curing process. Because it forms a protective film on the screed surface, CHRYSO® ScreedFinish EBA 20 slows down drastically the screed desiccation. It allows for screed hydration enhancement, reduces the risk for plastic shrinkage induced cracking or surface delamination and dusting. After setting, the screed surface abrasion resistance is also improved. CHRYSO<sup>®</sup> ScreedFinish EBA 20 includes a temporary white tracer which allows to identify easily the surface treated. The white color fades once the product is dry. By nature, CHRYSO<sup>®</sup> ScreedFinish EBA 20 doesn't require any removal (sanding or grinding) if the adhesion tests exhibit satisfactory results (see flooring solution manufacturer's recommendations). Due to its water-based technology, CHRYSO<sup>®</sup> ScreedFinish EBA 20 is user and environment friendly.



#### FIELDS OF APPLICATION

Cemfloor or Mobicem screeds

#### INDICATIVE INFORMATION

| liquid         |
|----------------|
| White          |
| 12 months      |
| 12,00 % ± 1,00 |
| 7,50 ± 0,50    |
|                |

#### METHOD OF USE

This product is ready to use. Spray on top of the screed immediately after the dappling brush or bar has been used so that the screed is protected against desiccation as soon as possible. We recommend a spraying equipment with flat spray nozzle and a minimum pressure of 3 bars (45 psi). Apply CHRYSO®ScreedFinish EBA 20 evenly on the screed (100 - 150 ml/m<sup>2</sup>) in order to obtain a uniform white color surface. A 2 crossed spray passes process is recommended to avoid any application gap. Rinse and wash the spraying equipment with water before the product dries up.

#### PRECAUTIONS

- Stir the product before use.
- Protect from frost.
- Avoid prolonged exposure to high temperatures.

# SAFETY

For further information, please refer to the safety data sheet on our internet site www.uk.chryso.com.

The information contained in this document is given to the best of our knowledge and is the result of extensive and controlled t esting. However, it cannot under any circumstances be considered as a warranty involving our liability in the case of misuse. Tests should be con ducted before the product is used to ensure that the methods and conditions of use of the product are satisfactory. Our specialists remain at the disposal of customers if they require help with the application of the product for their specific needs. www.chryso.uk CHEVSOLUK Ltd \_ 0. Brund Cloco. Dravtop Eiclde Industrial Ectato. NN11.9PR. Deventer Ulpited Kingdom Tál :±44.00.122727072 Fex:±44.

CHRYSO UK Ltd. - 9 Brunel Close, Drayton Fields Industrial Estate. NN11 8RB. Daventry, United Kingdom Tél.:+44 (0) 132770797 Fax:+44 (0) 13277079

